


## Sieve Analysis of Representative Sample

Mesh	%	Microns
40	93.5	420
50	53.4	297
80	20.9	177
100	8.2	149
Pan	3.6	-

120 mesh ----- 125 microns

200 mesh ---- -----74 microns



PIPE.RUBBER in Internal Olefin at 250F. 20 micron scale