



Original Test Results From Westport

Table #1 – Solubility and Percent Expansion of NER PipeRubber after three day tests

| <u>Temperature</u> | <u>IO Base</u> | <u>LAO Base</u> | <u>IO Base</u> | <u>#2 Diesel</u> |
|--------------------|----------------|-----------------|----------------|------------------|
| 200°F | 103% | 97% | 127% | 158% |
| 250°F | 109% | 109% | 97% | 152% |
| 300°F | 112%* | 112%* | 97% | 158%* |

- - Denotes partial solubility of PipeRubber in Base Fluid

Table #2 – Solubility and Percent Expansion of NER PipeRubber after seven day tests

| <u>Temperature</u> | <u>IO Base</u> | <u>LAO Base</u> | <u>IO Base</u> | <u>#2 Diesel</u> |
|--------------------|----------------|-----------------|----------------|------------------|
| 200°F | 82% | 97% | 103% | 106% |
| 250°F | 112% | 118% | 118% | 158% |
| 300°F | 127% | 97%* | 112%* | 103%* |